

High Permeability	Symbol	Unit	Measuring Conditions		Material
			settings	Temp.	T25C
Initial permeability	μ_i		796kHz;150mV	23°C	1800±25%
Saturation flux density	Bs	mT	f = 50Hz H = 4000A/m	23°C	310
				100°C	155
Remanent flux density	Br	mT	f = 50Hz H = 4000A/m	25°C	85
				100°C	45
Relative temp factor	α_{μ}	$\times 10^{-6}$	100kHz/1v	-20°C → 20°C	4
				60°C → 20°C	1
Coercive force	Hc	A/m	f = 50Hz H = 4000A/m	25°C	11
				100°C	7
Relative loss factor	$\tan \delta / \mu_i$	$\times 10^{-6}$	1MHz;150mV	25°C	2.3
Curie temperature	Tc	°C	1MHz;150mV		140
Electrical resistivity	ρ	Ω / m	1000V		10^6
Density	ds	g/cm3			5.2

