



Low Power Loss	Symbol	Unit	Measurtionsing Conditions		Material
			settings	Temp.	TL10D
Initial permeability	μ_i		796kHz;150mV	23°C	1000±25%
Saturation flux density	B_s	mT	H=4000A/m	23°C	370
				100°C	250
Relative temp factor	$\alpha_{\mu i}$	$\times 10^{-6}$	100kHz	20~60°C	5~15
Coercive force	H_c	A/m	H=4000A/m	23°C	16
Core loss volume density	P_{cv}	kW/m ³	50kHz;150mT	20°C	380
				100°C	300
Relative loss factor	$\tan \delta / \mu_i$	$\times 10^{-6}$	100kHz		15
Curie temperature	T_c	°C	100kHz		160
Electrical resistivity	ρ	Ω / m			10^{-6}
Density	d_s	g/cm ³			5.2

