

Material Characteristics



High Bm	Symbol	Unit	Measurtionsing Conditions		Material
			settings	Temp.	TB48
Initial permeability	μ_i		796kHz;150mV	23°C	300±25%
Saturation flux density	Bs	mT	H=4000A/m	23°C	470
				100°C	400
Relative temp factor	$\alpha_{\mu i y}$	$\times 10^{-6}$	100kHz	20~60°C	15~25
Coercive force	Hc	A/m	H=4000A/m	23°C	60
Core loss volume density	Pcv	kW/m3	50kHz;150mT	20°C	1150
				140°C	800
Relative loss factor	$\tan \delta / \mu_i$	$\times 10^{-6}$	100kHz		50
Curie temperature	Tc	°C	100kHz		300
Electrical resistivity	ρ	Ω / m			10^{-6}
Density	ds	g/cm3			5.2

