

Lead Free Adjustment	Symbol	Unit	Measurtionsing Conditions		Material
			settings	Temp.	H9-F
Initial permeability	μ_i		796kHz;150mV	23°C	45±25%
Saturation flux density	B_s	mT	H=4000A/m	23°C	400
				100°C	
Relative temp factor	α_{μ_i}	$\times 10^{-6}$	100kHz	20~60°C	20~60
Coercive force	H_c	A/m	H=4000A/m	23°C	350
Core loss volume density	P_{cv}	kW/m ³	50kHz;150mT	20°C	
				140°C	
Relative loss factor	$\tan \delta / \mu_i$	$\times 10^{-6}$	1MHz		100
Curie temperature	T_c	°C	100kHz		300
Electrical resistivity	ρ	Ω / m			10 ⁻⁶
Density	ρ_s	g/cm ³			5.0

